

Certification Report



Item Number **0206**

Manufacturing date **08.04.2016**

Charge No. **03/16**

Name

PANTAPOR 66 (LP)

Application

Air entraining agent acc. EN 934-2:T5

Range of dosage in mass-% of cement **0,05 - 0,8**

State liquid
Steadiness homogeneous
Colour light blue

Active substances surfactants

	Target	Tolerance (\pm)	Measured	Stat. Determ.
Density in g/ml	1	0,02	1,005	
Dry substance in mass-%	3,2	0,3	3,4	
pH-value	9,5 - 11,5		9,9	
Water-soluble chloride content in mass-% max	0,1			0,008
Total value of chlor in mass-% max	0,1			
Alkali content (Na ₂ O-equivalent) in mass-% max	1			0,42

This document was automatically generated on 13.04.2016 and is valid without signature