

# Certification Report



Item Number **0206**

Manufacturing date 22.10.2015

Charge No. 11/15

Name

**PANTAPOR 66 (LP)**

Application

**Air entraining agent acc. EN 934-2:T5**

Range of dosage in mass-% of cement 0,05 - 0,8

State liquid  
Steadiness homogeneous  
Colour light blue

Active substances surfactants

|   | Target     | Tolerance ( $\pm$ ) | Measured | Stat. Determ. |
|---|------------|---------------------|----------|---------------|
| Density in g/ml   | 1          | 0,02                | 1,005    |               |
| Dry substance in mass-%                                     | 3,2        | 0,3                 | 3,4      |               |
| pH-value  | 9,5 - 11,5 |                     | 10,2     |               |
| Water-soluble chloride content in mass-% max                | 0,1        |                     |          | 0,008         |
| Total value of chlor in mass-% max                          | 0,1        |                     |          |               |
| Alkali content (Na <sub>2</sub> O-equivalent) in mass-% max | 1          |                     |          | 0,44          |

This document was automatically generated on 05.11.2015 and is valid without signature